



## Chemical / Material Compatibility Table

### Ratings

- A** Excellent
- A1** Excellent <120°F (49°C)
- A2** Excellent <72°F (22°C)
- B** Good - Minor Effect, slight corrosion or discoloration.
- B1** Good <120°F (49°C)
- B2** Good <72°F (22°C)
- C** Fair - Moderate Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.
- C2** Fair <72°F (22°C)
- D** Severe Effect - not recommended for any use.
- Information not available

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Acetaldehyde	A	A	A	A	A	A	D	A	D	A	A	-	A
Acetamide	-	A	A	A	A	A	B	A	A	-	A	-	-
Acetate Solvent	-	A	A	A	A	A	D	C	C	A	A	A	A
Acetic Acid	A	A	A	A	A	A	B	C	C	A	B	A	A
Acetic Acid 20%	A	A	A	A	A	A	B	A	B	A	A	A	A
Acetic Acid 80%	A	A	A	A	A	A	B	C	C	A	B	A	A
Acetic Acid, Glacial	-	A	A	A	A	B	D	C	C	A	A	A	A
Acetic Anhydride	-	A	A	A	A	B	D	A	D	A	A	B	A
Acetone	A	A	A	A	A	A	D	A	D	A	A	A	A
Acetyl Bromide	-	-	-	A	-	-	-	A	-	-	-	-	-
Acetyl Chloride (dry)	-	-	A	A	-	D	A	A	D	A	A	B	-
Acetylene	A	A	A	A	A	A	A	A	B	-	A	A	-
Acrylonitrile	B	B	-	A	B	D	D	A	D	B	A2	A2	-
Adipic Acid	-	A1	-	A	A1	A1	A1	A	C	-	A1	-	-
Alcohols:Amyl	A	A	A	A	A	A	A	A	B	A	A	A	B
Alcohols:Benzyl	A	-	A	A	-	B	A	-	D	A	B	A	A
Alcohols:Butyl	A	A	A	A	A	A1	A	A	C	A	A	A	A
Alcohols:Diacetone	-	A	-	A	A	A	D	A	D	A	A	A	A
Alcohols:Ethyl	A	A	-	A	A	A	A	A	C	A	A	A	A
Alcohols:Hexyl	-	-	-	A	-	C	C	A	A	A	A	A	A
Alcohols:Isobutyl	-	A	-	A1	A	A	A	A	B	A	A	A	B
Alcohols:Isopropyl	A	A	-	A1	A	A	A	A	B	A	B	A	B
Alcohols:Methyl	A	A	A	A	A	A	C	A	A	A	A	A	B
Alcohols:Octyl	-	-	-	-	-	A	B	A	B	C	A	A	A
Alcohols:Propyl	A	A	A	A	A	A	A	A	A	A	A	A	A
Aluminum Chloride	A	A	A	A	A	A	A	A	A	A	B	B2	B
Aluminum Chloride 20%	A	A	A	A	A	A	A	A	A	A	C2	C2	B
Aluminum Fluoride	-	A	A	A	A	A	A	A	A	B	D	C	A
Aluminum Hydroxide	-	A	-	A	A	A	A	A	A	B	C2	A2	B2
Aluminum Nitrate	-	A1	-	A	A1	A1	A1	A	A1	-	A	-	A
Aluminum Potassium Sulfate 10%	A	A	-	A	A	A	A	A	A	C	A	A	A
Aluminum Potassium Sulfate 100%	A	A	-	A	A	A	A	A	A	C	B1	B	A
Aluminum Sulfate	A	A	A	A	A	A	A	A	A	B	B1	B	A
Alums	-	-	-	A	-	A2	A	A	A	B	A	A	A

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Amines	A	A	B	A1	A	B	D	A	D	B	A	B	B
Ammonia 10%	A	A	A2	A	A	A	D	-	A	A	A	A2	C
Ammonia Nitrate	-	-	A	A	-	A	D	-	C	-	A	A	-
Ammonia, anhydrous	A	A	A2	A	A	A	D	A	B	B	A1	A	C
Ammonia, liquid	B	A	A2	A	A	A	D	-	C	B	A1	B1	C
Ammonium Acetate	-	-	-	A	-	A	A	A	B	-	A	-	-
Ammonium Bifluoride	-	A	-	A	A	A1	A	A	B	B	B2	B	-
Ammonium Carbonate	-	A	A	A	A	A	A	A	B	B	B	B	A
Ammonium Caseinate	-	-	-	-	-	-	-	-	-	-	A	-	-
Ammonium Chloride	-	A	A	A	A	A	A	A	B	D	B1	B	B
Ammonium Hydroxide	A	A	A	A	A	A	B	A	D	B	A2	A	A
Ammonium Nitrate	A	A	A	A	A	A	A	A	A	B	A	A	A
Ammonium Oxalate	-	-	-	-	-	A	-	A	D	A	A	A	-
Ammonium Persulfate	-	A	-	A2	A	B	A	A	A	B	B	B	A
Ammonium Phosphate, Dibasic	-	A	A	A1	A	A	A	A	A	B	C	A2	A
Ammonium Phosphate, Monobasic	-	-	-	A	-	A	A	A	A	B	C	C	A
Ammonium Phosphate, Tribasic	-	-	-	A	-	A	A	A	A	B	B	-	A
Ammonium Sulfate	-	A	A	A	A	A	A	A	A	B	B	B	A
Ammonium Sulfite	-	D	-	A1	D	A2	D	A	A2	-	B	A	-
Ammonium Thiosulfate	-	-	-	-	-	A2	-	A	A	-	A	-	A
Amyl Acetate	A	A	A	A	A	A	D	A	D	A	A	A	A
Amyl Alcohol	A	A	A	A	A	A	A	A	B	A	A	A	B
Amyl Chloride	-	A	-	A	A	D	B2	A	D	A2	A1	A1	C
Aniline	A	A	A	A	A	B	A	A	D	B	B	A	C
Aniline Hydrochloride	-	D	-	A	D	B	A	A	D	D	D	B	A
Antifreeze	A	-	-	-	-	A	A	A	A	-	A	A	-
Antimony Trichloride	A	-	-	A	-	B2	A1	A	B	-	D	B	B
Aqua Regia (80% HCl, 20% HNO3)	D	D	D	A	D	C	B	A	D	C	D	D	A2
Arochlor 1248	A	-	-	A	-	B	A	A	C2	A	B	-	A2
Aromatic Hydrocarbons	A	-	-	-	-	D	A	A	D	-	C	-	-
Arsenic Acid	-	A	A	A	A	A1	A1	A	A1	B	A1	A2	B
Arsenic Salts	-	-	-	-	-	-	A	-	-	-	-	-	-
Asphalt	A	A	A	A2	A	D	A	-	B	-	A	A	-
Barium Carbonate	-	A	A1	A	A	A	A	A	A1	B	B	B2	A
Barium Chloride	A	A	A	A	A	A	A	A	A	B	A2	B	A
Barium Cyanide	-	-	-	A2	-	A	A	A	C	A	A1	A2	-
Barium Hydroxide	-	A	A	A	A	A	A	A	A	B	B	B2	B
Barium Nitrate	-	A	-	A2	A	A	A	A	A1	-	B	B	A
Barium Sulfate	-	A	A	A	A	A	A	A	A	A	B2	B	B
Barium Sulfide	A	A	-	A	A	A	A	A	A	-	B1	A2	A
Beer	A	A	A1	A	A	A	A	A	A	A2	A	A	B
Beet Sugar Liquids	-	A	-	A2	A	A	A	A	A	-	A	A	A
Benzaldehyde	A	A	A	A2	A	A	D	A	D	A	B	A	A
Benzene	A	A	A	A	A	D	A	A	D	B	B	A	A
Benzene Sulfonic Acid	D	A	A	A	A	D	A	A	D	B	B	A	B
Benzoic Acid	A	A	A2	A1	A	D	A	A	D	B2	B	B	A
Benzol	-	A	A	A	A	D	A	A	D	B	A2	A	A
Benzonitrile	-	A	-	A1	A	-	-	-	-	C	D	-	-
Benzyl Chloride	-	A2	-	-	A2	D	A1	A	D	C	B2	-	-
Bleaching Liquors	-	-	-	A	-	A	A	-	D	-	-	-	A
Borax (Sodium Borate)	A	A	A	A	A	A	A	A	B	B	A	A	B

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Boric Acid	A	A	A	A	A	A	A	A	A	A	A2	B1	A
Brewery Slop	-	-	-	-	-	-	A	-	A	-	A	A	-
Bromine	D	D	D	A	D	D	A	A	D	A	D	D	D
Butadiene	-	A	A2	A1	A	C	B	A	D	C	A2	A	-
Butane	A	A	A	A	A	D	A	A	A	A	A1	A	A
Butanol (Butyl Alcohol)	A	A	A	A1	A	A1	A	A	A	B	A2	A	B
Butter	-	-	-	A	-	A	A	A	A	-	A	-	-
Buttermilk	-	A	-	A	A	A2	A	-	A	A	A	-	-
Butyl Amine	A1	A1	D	A1	A1	-	D	A	-	B1	A	-	B1
Butyl Ether	-	A2	A1	A2	A2	D	D	-	B1	-	A2	-	-
Butyl Phthalate	A1	A1	A	A1	A1	B1	C2	A	D	B1	B1	-	B
Butylacetate	A	A	A	A	A	B	D	A	D	A	A	B2	A
Butylene	A	A	A	A	A	D	A	A	A	-	A	A	-
Butyric Acid	A	A	A	A1	A	B	B2	A	D	A2	B1	B	A
Calcium Bisulfate	-	-	-	-	-	A	-	-	A	-	A	-	-
Calcium Bisulfide	A	-	-	A	-	C	A	A	A2	A	B	B	A
Calcium Bisulfite	-	A	A	A	A	D	A	A	A	B	A	B2	A
Calcium Carbonate	A	A	-	A	A	A	A	A	A	B	B	B2	B
Calcium Chlorate	-	-	-	A	-	A	A	A	A	-	-	-	-
Calcium Chloride	A	A	A	A	A	A	A	A	A	A	B1	B	A
Calcium Hydroxide	A	A	A	A	A	A	A	A	A	A	B	B	A
Calcium Hypochlorite	A	A	A	A	A	B2	A	A	C2	B	B2	C	A2
Calcium Nitrate	A1	A1	A1	A1	A1	A1	A1	A	A1	B1	B1	-	B1
Calcium Oxide	A	-	A	A	-	A	B	A	A	A	A	A	A
Calcium Sulfate	A	A	A	A	A	A	A	A	A1	B	B	B2	A
Calgon	A	-	-	-	-	A	A	-	A	-	A	-	-
Cane Juice	-	-	-	A	-	A	A	-	A	-	A	A	-
Carbolic Acid (Phenol)	D	A	A	A	A	B	A	A	D	A	B	C	A
Carbon Bisulfide	D	-	-	-	-	D	A	A	C	-	B	B	-
Carbon Dioxide (dry)	A	A	A	A	A	B	B	A	A	A	A2	A	A
Carbon Dioxide (wet)	B	A	A	A	A	B	B	A	A	A	A2	A	A
Carbon Disulfide	D	A	A	A	A	D	A2	A	D	B	B	B	B
Carbon Monoxide	B	A	-	A	A	A	A	A	A	B	A	B	-
Carbon Tetrachloride	A	A	A	A	A	D	A	B	D	A2	B	B	A
Carbon Tetrachloride (dry)	-	A1	A1	A	A1	B2	A1	-	C2	B	B1	B	A1
Carbon Tetrachloride (wet)	-	A1	A1	A	A1	D	-	-	D	B	A1	A	A1
Carbonated Water	-	-	-	-	-	-	A	-	A	-	A	C	-
Carbonic Acid	A	A	A	A	A	B	A	A	D	A1	A	A	B2
Catsup	A	-	-	-	-	A	A	-	A	-	A	C	-
Chloric Acid	-	D	-	A	D	-	-	-	-	A1	C2	A2	-
Chlorinated Glue	-	-	-	-	-	B	A	-	B	-	A	A	-
Chlorine (dry)	A	A	D	A	A	A	A	A	B	A1	B	A	D
Chlorine Water	D	A	D	A	A	C	A	-	D	A1	C	A1	A
Chlorine, Anhydrous Liquid	D	A	D	A	A	B	A	A	D	D	C	D	D
Chloroacetic Acid	A	A	A	A	A	B	D	A	D	A2	A2	B2	A2
Chlorobenzene (Mono)	A	A	A	B	A	D	A	A	D	A	B	A	B
Chlorobromomethane	-	-	-	A	-	B	A	A	D	-	-	-	-
Chloroform	A	A	A	A2	A	D	A	A	D	A2	A	A	A1
Chlorosulfonic Acid	A	A	D	A	A	D	D	A	D	A2	B1	D	A
Chocolate Syrup	-	-	-	A	-	A	A	-	A	-	A	D	-
Chromic Acid 10%	D	A	A	A	A	C	B	A	D	A	B	D	B

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Chromic Acid 30%	A	A	B	A	A	B	A	A	D	D	B1	D	A
Chromic Acid 5%	A	A	A	A	A	A	A	A	D	B	A	D	A
Chromic Acid 50%	D	A2	A2	A	A2	B	A	A	D	B	B1	D	A1
Chromium Salts	-	-	-	-	-	-	-	A	-	-	-	-	-
Cider	-	-	-	-	-	A	A	-	A	-	A	A	-
Citric Acid	A	A	A	A	A	A	A	A	A	A	A1	B	A1
Citric Oils	A	-	-	-	-	B	A	-	A	-	A	D	-
Cloroxr (Bleach)	B	-	D	A	-	B	A	A	D	A	A	D	-
Coffee	-	-	-	-	-	A	A	-	A	A	A	D	A
Copper Chloride	A	-	A	A	-	A	A	A	A	-	D	D	D
Copper Cyanide	A	A	A	A	A	A	A	A	A	A2	B	B	B
Copper Fluoborate	-	-	-	-	-	-	A	-	B	B	D	D	-
Copper Nitrate	A	A	A	A	A	-	A	A	A	B1	A1	A	B
Copper Sulfate >5%	A	A	A	A	A	A	A	A	A	A	B	B	A
Copper Sulfate 5%	A	A	A	A	A	A	A	A	A	A	B	A	A
Cream	-	-	-	A	-	-	A	-	A	-	A	D	-
Cresols	A	A	A	-	A	D	A	A	D	B1	A	A1	B
Cresylic Acid	A	A	-	A	A	D	A	A	D	B2	A	A	A2
Cupric Acid	-	A1	A1	A	A1	A1	A1	-	B1	A2	B1	-	A1
Cyanic Acid	-	A	-	A	A	-	A	-	C	-	A	D	-
Cyclohexane	A	A	A	A	A	D	A	A	B	B	A	A1	A
Cyclohexanone	A	A	A	A	A	B	D	A	D	A2	A1	-	-
Detergents	A	A	A	A	A	A	A	A	A	B	A2	A1	A1
Diacetone Alcohol	-	A	-	A	A	A	D	A	D	-	B	-	-
Dichlorobenzene	A1	A1	-	A	A1	D	C	-	D	A2	B2	-	-
Dichloroethane	A	A	-	A2	A	-	C	A	D	A	B	-	B2
Diesel Fuel	A	A	A	A	A	D	A	A	A	B	A2	A	B
Diethyl Ether	A1	A1	A1	A	A1	D	D	A	D	B2	B1	-	A2
Diethylamine	A	A	-	D	A	B	A	A	C	A	A	A	A
Diethylene Glycol	-	A1	-	A1	A1	A1	A1	A	A1	B2	A	A	A2
Dimethyl Aniline	-	A1	A1	A	A1	B1	D	A	D	B1	B1	-	A1
Dimethyl Formamide	A	-	A	A	-	B	C	A	D	-	B	-	-
Diphenyl	-	-	-	A	-	D	A1	A	D	B	B	-	B
Diphenyl Oxide	-	-	A	A2	-	D	A	A	A	B2	A	A	A2
Dyes	-	-	-	-	-	-	A	-	-	-	A	C	-
Epsom Salts (Magnesium Sulfate)	A	A	A	A	A	A	A	A	A	B	B	C	A2
Ethane	B	A	-	A	A	D	A	A	A	-	A2	A	-
Ethanol	A	A	-	A	A	A	A	A	C	A	A	A	A
Ethanolamine	-	A	A	A2	A	B	D	A	B	B	A	A	B
Ether	A	A	A	A	A	C	C	A	D	B2	A	A	A2
Ethyl Acetate	A	A	A	A	A	B	D	A	D	A	B	A	A2
Ethyl Benzoate	-	-	-	A	-	-	A2	A	D	-	-	-	-
Ethyl Chloride	A	A	A	A	A	A	A	A	A	B2	A	A	A
Ethyl Ether	-	A1	A1	A	A1	D	D	A	D	B2	B	-	A2
Ethyl Sulfate	-	A	-	A	A	-	A	-	A	-	D	A	-
Ethylene Bromide	-	A	-	A	A	C	A	A	D	B	A	-	B
Ethylene Chloride	A	A	A	A	A	D	B	A	D	-	B	-	B2
Ethylene Chlorohydrin	A	A	-	A	A	B	A	A	D	B	B	-	B
Ethylene Diamine	A	-	A	A	-	A	B	A	A	C	B	-	A
Ethylene Dichloride	A	A	A	A	A	C	A	A	D	B	B	C	B
Ethylene Glycol	A	A	A	A	A	A	A	A	A	B2	B	A	A2

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Ethylene Oxide	A	A	D	A	A	C	D	A	D	A	B	A	-
Fatty Acids	A	A	-	A	A	D	A	A	B	A	A	C	B
Ferric Chloride	B	A	A	A	A	A	A	A	A	B1	D	D	A
Ferric Nitrate	A	A	A	A	A	A	A	A	A	B2	B	D	A
Ferric Sulfate	A	A	A	A	A	A	A	A	A	A2	A	D	A2
Ferrous Chloride	A	A	A	A	A	-	A	A	A	B2	D	C	A
Ferrous Sulfate	A	A	A	A	A	A	B	A	A1	B	B	D	A2
Fluoboric Acid	-	A	A	A	A	A1	B	A	A	A2	B	D	D
Fluorine	D	C	D	D	C	A2	C	B	D	B2	A	D	D
Fluosilicic Acid	-	A	A	A	A	A1	B2	A	A	B	B	D	D
Formaldehyde 100%	A	-	B	A	-	A	D	A	C	A	A	A	A
Formaldehyde 40%	A	A	A	A	A	A	A	A	B	B	A	A	B
Formic Acid	C	A	A	A	A	A	C	A	C	A	A2	C	C2
Freon 113	A	-	A	A	-	D	B	C	A	A	-	A	C
Freon 12	A	-	A	A	-	B	B	C	A	A	B	A	B
Freon 22	A	-	A	A	-	A	D	B	D	A	A	A	B
Freon TF	A	-	D	A	-	D	B	C	A	A	A	A	B
Freonr 11	A	-	A	A	-	D	B	C	B	A	A	A	B
Fruit Juice	A	-	-	A	-	-	A	-	A	A	A	C	A
Fuel Oils	A	A	A	B	A	D	A	A	A	A2	A	A	A
Furan Resin	-	-	A	A	-	C	D	A	D	B	A	A	-
Furfural	-	A	A	A	A	D	D	A	D	B	B	A	A
Gallic Acid	-	B	A	B	B	B	A	A	B	B2	B	A	B
Gasoline (high-aromatic)	-	A	A	B	A	D	A	-	A	A	A	A	B
Gasoline, leaded, ref.	A1	A1	A1	A	A1	D	A2	-	A1	A	A1	-	A
Gasoline, unleaded	-	A1	A1	A	A1	D	A2	A	A2	A	A1	A	A
Gelatin	A	A	-	A	A	A	A	A	A	A	A1	A	A
Glucose	-	A	B	A	A	A	A	A	A	A	A	A	A
Glue, P.V.A.	-	A	-	A	A	A	B	A	A	A	A1	A	A
Glycerin	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycolic Acid	-	A	A	A	A	A	A	A	A	A	A	-	A
Gold Monocyanide	-	-	-	D	-	-	A	-	A	-	A	A	-
Grape Juice	-	-	-	A	-	A	A	-	A	-	A	C	A
Grease	-	-	-	A	-	D	A	-	A	A	A	A	-
Heptane	A	A	A	A	A	D	A	-	A	A	A	A	A
Hexane	A	A	A	A	A	D	A	A	A	A	A	A	A
Honey	-	-	-	A	-	A	A	-	A	A	A	A	-
Hydraulic Oil (Petro)	B	B	D	A	B	D	A	A	A	A	A	A	-
Hydraulic Oil (Synthetic)	B	B	-	A	B	A	A	A	D	A	A	A	-
Hydrazine	A	-	-	A	-	A	A	A	B	-	A	D	-
Hydrobromic Acid 100%	D	A	A2	A	A	A	A	A	D	C	D	D	A
Hydrobromic Acid 20%	D	A	-	-	A	A	A	-	D	A	D	C	A
Hydrochloric Acid 100%	A	A	D	A	A	D	A	A	D	A	D	D	D
Hydrochloric Acid 20%	A	A	D	A	A	A	A	A	-	A2	D	D	D
Hydrochloric Acid 37%	A	A	D	A	A	C	A	A	B	B	D	D	D
Hydrochloric Acid, Dry Gas	A	A	A	A	A	-	-	A	-	A	D	D	C
Hydrocyanic Acid	A	A	B	A	A	B	A	A	B	A	A	D	B
Hydrocyanic Acid (Gas 10%)	A	-	-	A	-	A	A	A	B	-	-	D	A
Hydrofluoric Acid 100%	D	-	D	A	-	D	B	A	D	B	B2	D	D
Hydrofluoric Acid 20%	D	A	A	A	A	D	A	A	D	B	D	D	D
Hydrofluoric Acid 50%	D	A	A	A	A	D	B	A	D	B	D	D	D

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Hydrofluoric Acid 75%	D	A	B	A	A	C	B	A	D	B	D	D	D
Hydrofluosilicic Acid 100%	-	A	A2	A	A	A	A	A	B	B	D	D	D
Hydrofluosilicic Acid 20%	-	A	A	A	A	A	A	A	A	B	B2	D	D
Hydrogen Gas	-	A	A	A	A	A	A	A	A	A	A	A	A
Hydrogen Peroxide 10%	C	C	C	A	C	B	A	A	D	A	B	C	A
Hydrogen Peroxide 100%	C	C	C	A	C	D	A	A	D	A	A1	D	B
Hydrogen Peroxide 30%	C	C	C	A	C	B	A	A	D	A	B	B	B2
Hydrogen Peroxide 50%	C	C	-	A	C	B	A	A	D	A	A1	B	A
Hydrogen Sulfide (aqua)	A	A	A	A	A	B	D	A	D	A	A	D	B
Hydrogen Sulfide (dry)	A	A	A	A	A	B	D	A	D	A	A	D	A
Hydroquinone	-	A	-	A	A	D	B	A	D	B	B	-	B
Hydroxyacetic Acid 70%	-	-	-	A	-	A	A	A	A	-	-	D	A
Ink	-	-	-	A	-	-	A	-	A	-	C	D	-
Iodine	D	D	D	A	D	B	A	A	B	A	D	D	A
Iodine (in alcohol)	A	-	-	-	-	A	-	-	-	B	-	-	B
Iodoform	-	-	-	C	-	A	-	-	D	D	A	A	B
Isooctane	A1	A1	A1	A	A1	D	A2	A	A1	-	A2	-	-
Isopropyl Acetate	-	A	-	A	A	B	D	A	D	B	A	B	-
Isopropyl Ether	A	A	-	A2	A	D	D	A	B	A	A	A	-
Isotane	-	-	-	-	-	-	A	-	A	-	-	-	-
Jet Fuel (JP3, JP4, JP5)	A	A	A	A	A	D	A	A	A	A	A	A	A
Kerosene	A	A	A	A	A	D	A	A	A	B	A	A	A
Ketones	A	A	A	A	A	A	D	A	D	A	A	A	A
Lacquer Thinners	-	A	-	A	A	D	D	A	D	A	A	A	C
Lacquers	-	A	-	A	A	D	D	A	D	A	A	A	-
Lactic Acid	A	A	A	A	A	A	A	A	A	B2	B2	C	A
Lard	A	A	-	A	A	D	A	A	A	A	A	A	A
Latex	-	-	-	A	-	A	A	-	A	A	A1	A	-
Lead Acetate	A	A	A	A	A	A	D	A	B	B2	B2	A	A2
Lead Nitrate	-	A2	A	A2	A2	A1	A1	A	A1	B1	B2	-	-
Lead Sulfamate	-	-	-	B	-	A	A	A	B	-	C	-	-
Ligroin	A	-	-	A	-	D	A	A	A	-	A	A	-
Lime	-	A	-	A2	A	D	A	-	A	-	A	A	A
Linoleic Acid	-	A1	-	A	A1	D	B2	A	B2	-	A	-	-
Lithium Chloride	-	A1	-	A	A1	A2	A2	A	A1	-	A1	A	-
Lithium Hydroxide	-	B	-	A	B	-	-	A	C	B	B	D	-
Lubricants	A	A	A	A	A	D	A	A	A	A	A1	A	A
Lye: Ca(OH)2 Calcium Hydroxide	B	A	A	A	A	A	B2	A	A	A2	B	B	A
Lye: KOH Potassium Hydroxide	C	C	C	A	C	A1	B	A	B2	B2	A2	B	D
Lye: NaOH Sodium Hydroxide	B	-	A	A	-	B2	B2	A	A2	C	B2	D	B
Magnesium Bisulfate	-	A2	-	A	A2	-	-	-	B	-	A2	-	-
Magnesium Carbonate	-	-	-	A2	-	A	A	-	A1	B	B	A	A
Magnesium Chloride	B	A1	A2	A	A1	A	A1	A	A1	A1	D	C	A1
Magnesium Hydroxide	A	A	A	A	A	A	A	A	A	A	A2	A	A
Magnesium Nitrate	-	-	A	A	-	A	A	-	A	A	B	D	A
Magnesium Oxide	-	-	-	A	-	-	C	-	A	-	A	A	-
Magnesium Sulfate (Epsom Salts)	A	A	A	A	A	A	A	A	A	B	B	C	A2
Maleic Acid	A	A	B	A	A	D	A	A	D	B	B	A	A
Maleic Anhydride	-	-	-	A	-	D	A	A	D	-	A	-	-
Malic Acid	-	B	-	A	B	D	A	A	A	B	A1	A	A
Manganese Sulfate	-	A1	A1	A	A1	A1	A1	A	A1	A1	B1	C	A1

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Mash	-	-	-	-	-	A	A	-	A	-	A	A	-
Mayonnaise	-	-	-	A	-	-	A	-	C	A	A	D	-
Melamine	-	D	-	A	D	A	A	-	C	-	D	D	-
Mercuric Chloride (dilute)	C	C	C	A	C	A2	A	A	A	C	D	D	A2
Mercuric Cyanide	-	-	A	B	-	A2	A2	A	A	A	C	-	A
Mercurous Nitrate	-	C	-	A	C	A2	A2	A	B2	A2	A2	-	A2
Mercury	A	C	-	A	C	A	A	A	A	A1	A	D	A
Methane	B	B	-	A	B	D	A	A	A	A	A	A	-
Methanol (Methyl Alcohol)	A	A	A	A	A	A	C	A	A	A	A	A	B
Methyl Acetate	A	A	-	A	A	B	D	A	D	A	B	A	-
Methyl Acetone	-	A	-	A	A	A2	D	-	D	-	A	B	-
Methyl Acrylate	-	-	-	-	-	B	D	A	D	-	-	-	-
Methyl Alcohol 10%	A	A	A	A	A	A	C	A	A	A	A	A	B
Methyl Bromide	-	A	-	A	A	D	A	A	B2	-	A	-	-
Methyl Butyl Ketone	A	-	-	-	-	A2	D	A	D	-	A	A	-
Methyl Cellosolve	-	A	-	A	A	B1	D	A	A2	-	B	-	-
Methyl Chloride	-	A	B	A	A	D	A2	A	D	B	A	C	A
Methyl Dichloride	-	-	-	-	-	D	A2	A	D	-	-	-	-
Methyl Ethyl Ketone	A	A	A	A	A	A1	D	A	D	A	A	A	A
Methyl Ethyl Ketone Peroxide	-	-	-	-	-	D	D	A	D	-	-	-	-
Methyl Isobutyl Ketone	A	A	A	A	A	B2	D	A	D	A	B	C	A
Methyl Isopropyl Ketone	A	A	-	A	A	C2	D	A	D	-	A	-	-
Methyl Methacrylate	-	-	-	-	-	D	D	A	D	-	B	-	-
Methylamine	-	A1	-	A	A1	A2	D	A	B	-	A	D	-
Methylene Chloride	A	A	A	A	A	C2	B	A	D	B	B	A	B
Milk	A	A	-	A	A	A	A	A	A2	A	A	C	A
Mineral Spirits	-	A	A	A	A	D	A	-	A	B	A	C	B
Molasses	A	A	-	A	A	A2	A	-	A	A	A	D	A
Monochloroacetic acid	B1	B1	-	A1	B1	C	C	A	D	A1	A2	-	A1
Monoethanolamine	-	A	A	A	A	B	D	A	B2	-	A	-	B
Morpholine	-	A2	C	A1	A2	D	-	A	D	A2	A2	-	-
Motor oil	A1	A1	A1	A	A1	D	-	A	A	-	A1	-	A2
Mustard	-	A	-	A	A	A	D	-	B	A	A	D	A
Naphtha	A	A	A	B	A	D	A	A	A	B	A	B	B
Naphthalene	A	A	A	A	A	D	A	A	D	A	A	C	A
Natural Gas	A	-	-	A	-	D	A	A	A	-	A	-	-
Nickel Chloride	A	A	A	A	A	A2	A	A	A2	B	C	D	A
Nickel Nitrate	A	-	-	A1	-	A1	A1	A	A2	B1	B1	-	-
Nickel Sulfate	A	A	A	A	A	A2	A	A	A2	B	B2	C	B
Nitrating Acid (<15% HNO3)	-	-	C	A	-	-	-	-	-	A	D	D	C
Nitrating Acid (>15% H2SO4)	-	-	D	A	-	A2	-	-	D	A	C	D	C
Nitrating Acid (S1% Acid)	-	-	C	A	-	-	-	-	-	A	A	D	-
Nitrating Acid (S15% H2SO4)	-	-	C	A	-	-	-	-	-	A	C	D	A
Nitric Acid (20%)	A	A	C	A	A	A2	A	A	D	A2	A	D	A2
Nitric Acid (50%)	D	D	C	A	D	D	A	A	D	A2	A2	D	A2
Nitric Acid (5-10%)	A	A	B2	A	A	A2	A	A	D	A2	A	D	A2
Nitric Acid (Concentrated)	D	D	D	A	D	D	A	A	D	B2	A2	D	A2
Nitrobenzene	B	B	B	A	B	B2	B	A	D	D	B	C	A
Nitrogen Fertilizer	-	-	-	A	-	-	-	-	-	-	-	-	-
Nitromethane	A	A1	A1	A	A1	B1	D	A	D	A	A2	-	-
Nitrous Acid	-	-	-	A	-	A	B	A	-	D	B	A	-

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Nitrous Oxide	C	C	-	A	C	A	B	A	-	B	B	B	-
Oils:Aniline	A	-	-	A	-	B	C	-	D	B	A	A	D
Oils:Anise	-	-	-	-	-	-	-	-	-	-	A	A	-
Oils:Bay	-	-	-	-	-	-	A	-	-	-	A	A	-
Oils:Bone	-	-	-	A	-	-	A	-	A	-	A	A	-
Oils:Castor	A	-	-	A	-	B	A	A	B	-	A	A	A
Oils:Cinnamon	-	-	-	A	-	-	A	-	-	-	A	A	-
Oils:Citric	-	-	-	A	-	B	A	-	D	A	A	D	-
Oils:Clove	-	-	-	A	-	-	A	-	A	A	A	A	-
Oils:Coconut	A	-	-	A	-	D	A	A	A	A	A	A	-
Oils:Cod Liver	-	-	-	A	-	A	A	A	A	A	A	A	-
Oils:Corn	-	-	-	A	-	C	B	A	D	A	A	C	-
Oils:Cottonseed	-	A	A	A	A	D	A	A	A	A	A	A	A
Oils:Creosote	A	A	-	A	A	D	A	A	D	B	B	C	A
Oils:Diesel Fuel (20, 30, 40, 50)	A	A	A	A	A	D	A	A	A	B	A	A	B
Oils:Fuel (1, 2, 3, 5A, 5B, 6)	A	A	A	A	A	D	B	A	B	A2	A	A	B
Oils:Ginger	-	-	-	A	-	A	A	-	A	-	D	D	-
Oils:Hydraulic Oil (Petro)	A	B	D	A	B	D	A	A	A	A	A	A	-
Oils:Hydraulic Oil (Synthetic)	A	B	-	A	B	A	A	A	D	A	A	A	-
Oils:Lemon	-	-	-	A	-	D	A	-	-	-	A	A	-
Oils:Linseed	A	A	B	A	A	D	A	A	A	B	A	A	A
Oils:Mineral	A	A	A	A	A	D	A	A	A	A	A	A	A
Oils:Olive	-	A	-	A2	A	D	A	A	D	A	A	A	A
Oils:Orange	-	-	-	-	-	-	A	-	A	A	A	A	A
Oils:Palm	-	-	-	A	-	A	A	-	A	-	A	A	A
Oils:Peanut	A	-	-	A	-	D	A	A	A	-	A	A	A
Oils:Peppermint	-	-	-	A	-	-	A	-	D	-	A	A	-
Oils:Pine	-	-	-	A	-	D	A	A	D	-	A	D	A
Oils:Rapeseed	-	-	-	A	-	A	A	A	D	-	A	A	A
Oils:Rosin	-	A	-	A	A	-	A	-	A	A	A2	A	-
Oils:Sesame Seed	-	-	-	A	-	-	A	-	A	-	A	A	A
Oils:Silicone	A	A	A2	A	A	A	A	A	A	A	A	A	-
Oils:Soybean	A	A	-	A	A	C	A	A	A	A	A	A	A
Oils:Sperm (whale)	-	-	-	A	-	-	A	-	A	-	A	A	A
Oils:Tanning	-	-	-	-	-	-	A	-	A	-	A	A	-
Oils:Transformer	A	A	-	A	A	D	A	A	A	-	A	A	-
Oils:Turbine	-	-	-	A	-	A	A	A	B	-	A	A	A
Oleic Acid	A	A	A	A	A	B	B	A	B	A1	A	C	B
Oleum 100%	-	D	D	A	D	D	A	A	D	D	A	D	D
Oleum 25%	-	D	D	A	D	D	A	A	D	A	B	D	D
Oxalic Acid (cold)	A	A	A	A2	A	A	A	A	D	B	A	A	A
Ozone	A	-	-	A	-	A	A	A	D	-	A	-	-
Palmitic Acid	-	A1	-	A1	A1	B2	A2	A	A1	B	A2	-	-
Paraffin	A	A	-	A	A	D	B	-	B	B	A	A	A
Pentane	A	A	-	A	A	D	A	A	A	A	C	C	-
Perchloric Acid	A	A	-	A	A	B	A	A	D	B	C	-	D
Perchloroethylene	A	A	A	A	A	D	A	A	C	B	A2	D	A
Petrolatum	A	A	-	C	A	A	A	A	A	A	A	A	-
Petroleum	A1	A1	-	A1	A1	D	A1	A	A1	-	A2	-	A2
Phenol (10%)	-	A	A	A	A	B	A	A	D	B	B	C	B
Phenol (Carbolic Acid)	D	A	A	A	A	B	A	A	D	A	B	C	A



Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Phosphoric Acid (>40%)	B	B	B	A	B	B	A	A	D	A1	D	D	C
Phosphoric Acid (crude)	A	A	A	A	A	B	A	-	D	A1	B	D	C
Phosphoric Acid (molten)	-	-	-	-	-	-	-	-	-	C	C	A	D
Phosphoric Acid (S40%)	-	A	A	A	A	B	A	-	D	A1	C	D	C
Phosphoric Acid Anhydride	-	-	D	-	-	-	-	-	D	-	-	A	D
Phosphorus	-	D	-	A1	D	-	-	-	-	A1	A1	-	-
Phosphorus Trichloride	A	A	A	A1	A	A2	A2	A	D	A1	A1	-	A
Photographic Developer	-	A	-	A	A	B	A	A	A	B	A	D	A
Photographic Solutions	A1	A1	A1	A1	A1	A2	B2	A	B	B1	-	-	A2
Phthalic Acid	A2	A2	-	A1	A2	A2	A2	A	D	B1	A	-	A
Phthalic Anhydride	-	A	-	A	A	A	A	A	D	A	A	B	-
Picric Acid	A	A	A	A	A	B	A	A	C	B	B	D	A
Plating Solutions, Antimony Plating 130°F	-	-	-	A	-	-	A	-	A	A	A	A	A
Plating Solutions, Arsenic Plating 110°F	-	-	-	A	-	-	A	-	A	A	A	A	A
Plating Solutions, Brass Plating: High-Speed Brass Bath 110°F	-	A	-	A	A	-	A	-	A	A	A	A	A
Plating Solutions, Brass Plating: Regular Brass Bath 100°F	-	A	-	A	A	-	A	-	A	A	A	A	A
Plating Solutions, Bronze Plating: Cu-Cd Bronze Bath R.T.	-	-	-	A	-	A	A	-	A	A	A	A	A
Plating Solutions, Bronze Plating: Cu-Sn Bronze Bath 160°F	-	-	-	A	-	A	A	-	A	A	A	A	D
Plating Solutions, Bronze Plating: Cu-Zn Bronze Bath 100°F	-	-	-	A	-	-	A	-	A	A	A	A	A
Plating Solutions, Cadmium Plating: Cyanide Bath 90°F	-	-	-	A	-	-	A	-	A	A	A	A	A
Plating Solutions, Cadmium Plating: Fluoborate Bath 100°F	-	-	-	A	-	-	A	-	B	D	A	A	D
Plating Solutions, Chromium Plating: Barrel Chrome Bath 95°F	-	-	-	A	-	-	C	A	D	D	D	D	C
Plating Solutions, Chromium Plating: Black Chrome Bath 115°F	-	-	-	A	-	-	C	A	C	D	C	C	A
Plating Solutions, Chromium Plating: Chromic-Sulfuric Bath 130°F	-	-	-	A	-	-	C	A	D	D	C	C	A
Plating Solutions, Chromium Plating: Fluoride Bath 130°F	-	-	-	A	-	-	C	A	D	D	D	D	C
Plating Solutions, Chromium Plating: Fluosilicate Bath 95°F	-	-	-	A	-	-	C	A	D	D	C	C	C
Plating Solutions, Copper Plating (Acid): Copper Fluoborate Bath 120°F	-	-	-	A	-	-	A	-	B	D	D	D	D
Plating Solutions, Copper Plating (Acid): Copper Sulfate Bath R.T.	-	-	-	A	-	-	A	-	A	D	D	D	A

	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
<b>Chemical</b>													
Plating Solutions, Copper Plating (Cyanide): Copper Strike Bath 120°F	-	-	-	A	-	-	A	-	A	A	A	-	-
Plating Solutions, Copper Plating (Cyanide): High-Speed Bath 180°F	-	-	-	A	-	-	A	-	A	A	A	-	D
Plating Solutions, Copper Plating (Cyanide): Rochelle Salt Bath 150°F	-	-	-	A	-	-	A	-	A	A	A	-	D
Plating Solutions, Copper Plating (Misc): Copper (Electroless)	-	-	-	A	-	-	A	-	D	-	-	-	A
Plating Solutions, Copper Plating (Misc): Copper Pyrophosphate	-	-	-	A	-	-	A	-	A	A	A	A	A
Plating Solutions, Gold Plating: Acid 75°F	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Gold Plating: Cyanide 150°F	-	-	-	A	-	-	A	-	A	A	A	-	A
Plating Solutions, Gold Plating: Neutral 75°F	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Indium Sulfamate Plating R.T.	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Iron Plating: Ferrous Am Sulfate Bath 150°F	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Iron Plating: Ferrous Chloride Bath 190°F	-	-	-	A	-	-	A	-	B	D	D	-	A
Plating Solutions, Iron Plating: Ferrous Sulfate Bath 150°F	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Iron Plating: Fluoborate Bath 145°F	-	-	-	A	-	-	A	-	B	B	D	-	D
Plating Solutions, Iron Plating: Sulfamate 140°F	-	-	-	A	-	-	A	-	A	B	D	-	A
Plating Solutions, Iron Plating: Sulfate-Chloride Bath 160°F	-	-	-	A	-	-	A	-	B	D	D	-	A
Plating Solutions, Lead Fluoborate Plating	-	-	-	A	-	-	A	-	B	A	C	-	D
Plating Solutions, Nickel Plating: Electroless 200°F	-	-	-	A	-	-	A	-	D	-	-	-	-
Plating Solutions, Nickel Plating: Fluoborate 100-170°F	-	-	-	A	-	-	A	-	B	A	C	-	D
Plating Solutions, Nickel Plating: High-Chloride 130-160°F	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Nickel Plating: Sulfamate 100-140°F	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Nickel Plating: Watts Type 115-160°F	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Rhodium Plating 120°F	-	-	-	A	-	A	A	-	A	D	D	-	D

	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
<b>Chemical</b>													
Plating Solutions, Silver Plating 80-120°F	-	-	-	A	-	A	A	-	A	A	A	-	A
Plating Solutions, Tin-Fluoborate Plating 100°F	-	-	-	A	-	-	A	-	B	A	C	-	D
Plating Solutions, Tin-Lead Plating 100°F	-	-	-	A	-	-	A	-	B	A	C	-	D
Plating Solutions, Zinc Plating: Acid Chloride 140°F	-	-	-	A	-	-	A	-	A	D	D	-	A
Plating Solutions, Zinc Plating: Acid Fluoborate Bath R.T.	-	-	-	A	-	-	A	-	B	A	C	-	D
Plating Solutions, Zinc Plating: Acid Sulfate Bath 150°F	-	-	-	A	-	-	A	-	A	A	C	-	A
Plating Solutions, Zinc Plating: Alkaline Cyanide Bath R.T.	-	-	-	A	-	-	A	-	A	A	A	-	A
Potash (Potassium Carbonate)	A	A	-	-	A	A2	A	A	A	B	B	B	A
Potassium Bicarbonate	A	A	A	A	A	A	A	A	A	B	B	B	A
Potassium Bromide	-	A	A	A	A	A2	A	A	A	B	B	B	A
Potassium Chlorate	A1	A1	A1	A	A1	A2	A	A	A2	B	B	B	A
Potassium Chloride	A	A	A	A	A	A2	A	A	A2	A	A2	A	A
Potassium Chromate	-	A	-	A2	A	A1	A	A	A2	A	B2	B	-
Potassium Cyanide Solutions	-	A	A	A	A	A2	A	A	A2	B	B2	B	A
Potassium Dichromate	-	A	A	A	A	A2	A	A	A2	B	B2	B	A
Potassium Ferricyanide	A1	A1	-	A1	A1	A	A	A	D	B1	B2	B	A1
Potassium Ferrocyanide	A	A	-	A	A	A	A	-	D	B	B	B	A
Potassium Hydroxide (Caustic Potash)	C	C	C	A	C	A1	B	A	B2	B2	A2	B	D
Potassium Hypochlorite	-	-	A	A1	-	A2	-	A	A2	B1	B	B	A2
Potassium Iodide	-	A2	A2	A1	A2	A	A	A	A2	A1	A2	A	A2
Potassium Nitrate	A	A	A	A	A	A	A	A	A1	B2	B	B	A
Potassium Oxalate	-	A2	-	A1	A2	-	-	-	-	A2	B2	B	A2
Potassium Permanganate	B2	B2	B2	A	B2	A	A	A	C	A2	B	B	A
Potassium Sulfate	A	A	A	A	A	A2	A1	A	A1	B2	A	A	A
Potassium Sulfide	A	A	A	A	A	A	A	A	A	-	B	A	A
Propane (liquefied)	A	A	-	A	A	D	A	A	A	A	A	A	-
Propylene	-	A1	-	A1	A1	D	A2	A	D	-	A2	A	-
Propylene Glycol	-	-	-	A	-	A	A	A	A	B	B	A	A
Pyridine	A	A	A	A	A	B	D	A	D	B	A	A	B
Pyrogallic Acid	-	A	-	A	A	B	A	A	-	B	B	B	A
Resorcinol	A1	A1	-	A1	A1	B2	A2	A	-	-	-	-	-
Rosins	-	A	-	A	A	-	A	-	A1	-	A2	B	-
Rum	-	-	-	-	-	A	A	-	A	-	A	-	-
Rust Inhibitors	-	-	-	-	-	-	A	-	A	-	A	B	-
Salad Dressings	-	-	-	-	-	-	A	-	A	-	A	B	-
Salicylic Acid	A1	A1	-	A1	A1	A	A2	A	B	A1	B1	B	A2
Salt Brine (NaCl saturated)	A1	A1	A1	A1	A1	A	A1	A	A	A1	A1	B	A1
Sea Water	A	A	A	A	A	A1	A	A	A1	A	C	A	A
Shellac (Bleached)	-	A	-	A	A	A1	A	-	A1	-	A	A	-
Shellac (Orange)	-	A	-	A	A	A	A	-	A	-	A	A	-
Silicone	A	A	A2	A	A	A	A	A	A	-	A	A	-

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Silver Bromide	-	-	-	A	-	-	-	-	-	A	D	A	-
Silver Nitrate	A	A	A	A	A	A	A	A	B	A	B	C	A
Soap Solutions	A	A	A	A	A	A	A	A	A	A	A2	A	A
Soda Ash (see Sodium Carbonate)	A	-	A	A	-	A1	A	A	A2	-	A	A	-
Sodium Acetate	A	A	A	A	A	A	D	A	B	A	B2	A	A
Sodium Aluminate	-	A	A	A	A	A	A	A	A	B	A	B	A
Sodium Benzoate	A1	A1	-	A1	A1	A	A2	A	B	A2	-	-	A2
Sodium Bicarbonate	A	A	A	A	A	A1	A	A	A2	B2	A2	A	A1
Sodium Bisulfate	A	A	A	A	A	A1	A	A	B1	B1	C	C	A
Sodium Bisulfite	A	A	A	A	A	A1	A	A	A1	B	B2	B	A
Sodium Borate (Borax)	A	A	A	A	A	A	A	A	A2	A	B	A	B
Sodium Bromide	-	A1	-	A1	A1	A	A2	A	-	-	C	B	A2
Sodium Carbonate	A	A	A	A	A	A1	A	A	A	A	A	B	A2
Sodium Chlorate	C	C	C	A	C	A	A	A	B	B2	B2	B	A
Sodium Chloride	A	A	A	A	A	A	A	A	A	A	B	B	A
Sodium Chromate	A	A	A	A	A	-	A	A	A	A	B	B	-
Sodium Cyanide	A	A	A	A	A	A1	A1	A	A	A	B2	A	A
Sodium Ferrocyanide	A	A	-	A	A	A	A	A	A	A	B	-	-
Sodium Fluoride	A	A	-	A2	A	A	A	A	A2	A	D	C	A
Sodium Hydrosulfite	A	-	-	A	-	B	A	A	C	A	-	C	-
Sodium Hydroxide (20%)	A1	A1	A1	A	A1	B	C	A	A	B	B1	A1	A2
Sodium Hydroxide (50%)	A	-	A	A	-	B2	D	A	A2	C	B2	B1	B
Sodium Hydroxide (80%)	A1	A1	A1	A2	A1	B2	D	A	D	A2	B2	D	D
Sodium Hypochlorite (<20%)	B	B	A	A	B	B	A2	A	B	A	C	D	C
Sodium Hypochlorite (100%)	C	C	C	A	C	B2	A2	A	D	B	D	D	C
Sodium Hyposulfate	-	-	-	A	-	-	-	-	-	-	A	D	-
Sodium Metaphosphate	A	A	-	A	A	A	A	A	A	-	A	A	-
Sodium Metasilicate	A	-	-	A	-	A2	A	A	A	A	A	B	-
Sodium Nitrate	C	C	C	A	C	A	A	A	A2	B	B2	C	A
Sodium Perborate	C	C	-	A	C	A	A	A	B	B	B	D	-
Sodium Peroxide	A	A	-	A	A	A	A	A	B	B	A	D	-
Sodium Polyphosphate	A	A	-	A	A	A	A	-	A	A	B	C	A
Sodium Silicate	A	A	A	A	A	A	A	A	A	B	B	A	A
Sodium Sulfate	A	A	A	A	A	A	A	A	A	B	B2	C	A
Sodium Sulfide	A	A	A	A	A	A1	A1	A	A	B2	D	D	A
Sodium Sulfite	A	A	-	A	A	A	A1	A	A	B	A	C	A
Sodium Tetraborate	A	A	-	A	A	A	A	A	A	-	A	-	-
Sodium Thiosulfate (hypo)	A	A	A	A	A	A1	A	-	B	A1	B	D	A
Sorghum	-	-	-	-	-	-	A	-	A	-	A	D	-
Soy Sauce	-	-	-	-	-	-	A	-	A	-	A	A	-
Stannic Chloride	A	A	A	A	A	A	A	A	A	B	D	D	A
Stannic Fluoborate	-	-	-	-	-	-	A	-	A	-	A	D	-
Stannous Chloride	A	-	A2	A	-	C	A	A	A	B	A1	D	A
Starch	A	A	-	A	A	A	A	-	A	-	A	A	-
Stearic Acid	A	A	-	A	A	B	A2	A	B	B	A	C	A
Stoddard Solvent	A	A	A	A	A	D	A	A	A	A	A	A	A
Styrene	A	A	-	A	A	D	B	A	D	D	A	A	-
Sugar (Liquids)	-	A	-	A	A	A	A	-	A	A	A	A	-
Sulfate (Liquors)	-	A	-	A	A	A	A2	A	A1	B	B	D	-
Sulfur Chloride	D	D	-	A	D	D	A	A	D	A	D	D	D
Sulfur Dioxide	A	A	A	A	A	A1	A	A	D	C	A2	B	A

Chemical	Materials												
	Micropump Gears					Micropump Seals				Micropump Body			
	Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium
Sulfur Dioxide (dry)	A	A	A	A	A	A1	A	A	D	B	A	A	A
Sulfur Hexafluoride	A	-	-	-	-	B	-	B	B	-	-	-	-
Sulfur Trioxide	A	B	-	A	B	C2	A	A	D	-	C	A	-
Sulfur Trioxide (dry)	D	D	-	A	D	C2	A	-	D	B	A	B	D
Sulfuric Acid (<10%)	A	A2	A	A	A2	A	A	A	A2	B2	B	D	D
Sulfuric Acid (10-75%)	D	A2	A	A	A2	B1	A1	A	B2	B2	D	A1	D
Sulfuric Acid (75-100%)	D	C2	C2	A	C2	B2	A2	A	C	B2	D	A1	D
Sulfuric Acid (cold concentrated)	D	D	D	A	D	C	B	A	D	A2	B	A1	D
Sulfuric Acid (hot concentrated)	D	D	D	A	D	D	A1	-	D	D	C	D	D
Sulfurous Acid	A	A	A	A	A	B	A	A	B2	B	B	D	A
Sulfuryl Chloride	-	-	-	A	-	-	-	-	-	-	-	-	-
Tallow	A	A	-	A	A	A	A	A	A	-	A	-	-
Tannic Acid	-	A	A	A	A	A	A	A	A	B2	A	A	A
Tanning Liquors	-	A	-	A	A	B	A	-	B2	B	A1	A	A
Tartaric Acid	A	A	A	A	A	B	A	A	A	B	C2	A	A2
Tetrachloroethane	-	A	-	A	A	D	A	A	D	A	A	-	A
Tetrachloroethylene	A	A	-	A	A	D	A	A	D	-	A	-	-
Tetrahydrofuran	A	A	A	A	A	D	D	A	D	A	A	D	B
Tin Salts	A	-	-	A	-	B	A	-	A	C	D	-	A
Toluene (Toluol)	A	A	A	A	A	D	C	A	D	A	A	A	A
Tomato Juice	-	A	A	A	A	A	A	-	A	-	A	C	-
Trichloroacetic Acid	-	A	A	A	A	B	C	A	-	B	C	-	D
Trichloroethane	A	A	-	A	A	D	A	A	D	A	B	A	A
Trichloroethylene	A	A	A2	A	A	D	A	A	D	A	B	A	A
Trichloropropane	-	-	-	A2	-	-	A	A	D	A	A	A	-
Tricresylphosphate	-	A	-	A	A	A	A1	A	D	A	B	A	B
Triethylamine	-	A	-	A	A	A	D	A	C	-	A	A	-
Trisodium Phosphate	A	A	A	A	A	A	A	A	A	A	B	C	-
Turpentine	A	A	A	A	A	D	A	A	-	B	A	C	B
Urea	A	A	A	A	A	A	A	-	B	B	B	-	A
Uric Acid	-	A	-	A	A	-	-	A	-	B	B	-	A
Urine	-	A	-	A2	A	A2	A2	-	A2	-	A	C	-
Varnish	A	A	-	A	A	D	A	A	B	A	A	A	-
Vegetable Juice	-	-	-	A	-	A	A	-	A1	-	A	C	-
Vinegar	A	A	A	A	A	A	A	A	B	A	A	C	A
Vinyl Acetate	-	A1	-	A1	A1	B1	A2	A	D	-	B	-	-
Vinyl Chloride	A1	A1	-	A1	A1	C	A2	A	D	A1	A2	-	A
Water, Acid, Mine	-	A	A	A	A	A	A	-	A	A	B	C	A
Water, Deionized	-	A1	A1	A1	A1	A2	A2	-	A2	A1	A1	-	A1
Water, Distilled	A	A	A	A	A	A	A	-	A	A	A	D	A
Water, Fresh	A	A	A	A	A	A	A	A	A	A	A	A	A
Water, Salt	A	A	A	A	A	A	A	-	A	A	B	D	A
Weed Killers	-	-	-	-	-	-	A	-	A	-	A	C	-
Whey	-	-	-	A	-	-	A	-	A	-	A	-	-
Whiskey & Wines	A	A	-	A	A	A	A	-	A	-	A	C	A
White Liquor (Pulp Mill)	-	A	-	A	A	-	A	-	A	A	A	D	-
White Water (Paper Mill)	-	-	-	-	-	-	A	-	-	-	A	A	-
Xylene	A	A	A	A	A	D	B	A	D	A	B	A	A
Zinc Chloride	A	A	A	A	A	A	A	A	A	B	B	D	A2
Zinc Hydrosulfite	-	-	A	A	-	A	-	A	A	-	A	D	-
Zinc Sulfate	A	A	A	A	A	A	A	A	A	A1	A	C	A1

Materials												
Micropump Gears					Micropump Seals				Micropump Body			
Micropump PEEK	Carbon Graphite	Micropump PPS	PTFE	Carbon Graphite	EPDM	Viton	Kalrez	Buna N	Hastelloy C	SS316	Alloy 20	Titanium

**Chemical**

**NOTE**

This information was collected by Micropump from reputable sources and modified to reflect Micropump specific material characteristics and our experience making gear pumps from these materials. This data should only be used as a guide in selecting wetted pump materials with appropriate chemical compatibility. It is not a guarantee of performance under the specific conditions of your application.

Micropump does not warrant (neither express nor implied) that the information in this chart is accurate or complete or that any material is suitable for any purpose.



# OFFICIAL DISTRIBUTORS FOR:

